

Technical Data Sheet NR 12565

WHITE EXTRACOVERING POLYURETHANE GLOSS

Creation date: 02/03/2010 Revision date: 05/06/2012, version 2

ICA S.p.a. Via S. Pertini n. 52, Zona Ind.le A 62012 Civitanova Marche (MC) - Italy
Tel. +39 0733 8080 Fax. +39 0733 808140

PRODUCT: LP155P WHITE EXTRACOVERING POLYURETHANE GLOSS

DESCRIPTION: white pigmented extracovering polyurethane gloss top coat

USE: kitchen cupboard doors and other wooden objects for lacquered cycles

SPECIFICATIONS OF SUPPLIED PRODUCT

Physical state: white liquid
Solid content %: 74.8 ± 2

Gloss: 90±5 gloss

SUBSTRATE: white polyurethane or polyester base coats

APPLICATION: by spray and by curtain coater

HARDENER: C152AP or C153AP at 50% in weight or at 70% in volume. If it is necessary to quicken drying times of the product, anti-yellowing catalyst C152AP100 can be used at 100% in weight

DRYING:

Dust free: 35 minutes
Touch dry: 90 minutes

DILUTION: D1010 or D1015 at 20-40%

QUANTITY TO APPLY: 110-150 g/m²

NUMBER OF COATS: one or two coats

INTERVAL BETWEEN COATS: minimum one hour

POT LIFE at 20°C: 2 hours

STORAGE INFORMATION: store in a cool place away from direct sunlight

SHELF LIFE AT 20°C: 365 days in correctly stored closed tin

NB: mix the product well before use

SPECIFICATIONS OF SUPPLIED PRODUCT

CHARACTERISTICS	UNITS	VALUE	METHOD
Specific gravity at 20°C:	g/ml	1.45 ± 0.05	MP01
Visc. F.C. 4 at 20°C:	sec	110 ± 10	MP04
Fineness:	µm	20 max.	MP12

The quality control value of the viscosity refers to the product immediately after checking. Any variations of the data specified in the technical data sheet could be due to circumstances such as length and conditions of storage.

Always verify the suitability of the product for the job to be done before application. We can not accept responsibility for the outcome.

The information contained in this technical data sheet, as well as any verbal information, is given to the best of our knowledge. We do not accept responsibility for obsolete or incorrect information. The information is to be considered obsolete when a new technical data sheet is issued. Please feel free to contact us to request the latest edition.