



## VINYL ACRYLIC/ACRYLIC EGGSHELL LATEX 1100 SERIES TECHNICAL DATA

A premium high hiding, spatter resistant Latex Eggshell finish. Dries to a beautiful Eggshell finish quickly and uniformly with virtually no odour. Used on areas where some washability is needed in lighter traffic areas or the sheen is desired for effect. Living room, dining room, dens and some bedrooms.

**SPECIFIC GRAVITY: 1.32.**

**FLASH POINT: NONE**

**GLOSS: 5-8 @ 60°, 20-30 @ 85°.**

**VISCOSITY: 100-105 KU**

**AGRICULTURE CANADA: Approved for food storage.**

### **SURFACE PREPARATION:**

All surfaces should be clean, dry and free of dust, grease, wax or other contaminants. Previously painted surface should be scrapped, cleaned and repaired where necessary with a spackling compound to ensure a smooth, sound surface before applying paint. Dull glossy surfaces by fine sandpaper. Prime where necessary. Shellac all knots and prime bare wood with an oil based primer or Pro-Stick-Tek 100% Acrylic Primer. Plaster must age at least 30 days and be thoroughly dry before painting. Metal surfaces should be removed of all rust and cleaned. Prime with an appropriate metal primer.

**APPLICATION:** Apply at air temperature of 10 C or higher. May be applied by brush, roller, or spray. Stir product with a circular, lifting motion prior to using the product. Brush a 4-foot section on the edges and roll in the middle using “W’s” or “M’s”. Fill in the section and always finish on the down stroke from the very top of the wall to the very bottom in one clean motion. Overlap slightly and continue until the wall is finished.

**Brush-**Nylon or Polyester is recommended.

**Roller-** Smooth to medium (5mm-10mm) sleeve is recommended.

**Spray-** (Airless Equipment) - .015" to .019" tip size.

- 2300-2700 p.s.i.

\*Spray recommendations will vary according to manufacturer.

**DRY TIME:** Dry to touch 30 minutes. Recoat 2-4 hours.

**SPREADING RATE:** Up to 440 Sq. ft/ 4 litres yields approx. 4 mils wet (1.4 mils dry) film per coat. Surface texture and porosity will affect actual yield.

**CLEAN UP:** Use warm soapy water to wipe spots and smears immediately and to clean tools.

**THINNING:** Not normally recommended but water if necessary.

**CLEANING MAINTENANCE:** After a period of 30 days, surfaces may be washed periodically. Abrasive cleaners are not recommended.