



## **100% ACRYLIC LOW LUSTRE LATEX 1540 SERIES TECHNICAL DATA**

This Premium coating has many features that make it one of the best coatings on the market. Excellent adherence, scrubbable, and splatter-free makes this paint excellent for kitchens, and bathrooms where mould and mildew resistance are required. Very high in hiding that dries quickly and has a low odour. Excellent for virtually any room, including doors and trims. Stain resistant. Can be applied to a surface temperature of 0°C, instead of normally 10°C of any other type of regular Latex or most Acrylics.

**SPECIFIC GRAVITY: 1.33**

**FLASH POINT: NONE**

**GLOSS: 20-30@60°, 45-65@85°.**

**VISCOSITY: 90-95 KU**

**AGRICULTURE CANADA: Approved for food storage.**

### **SURFACE PREPARATION:**

All surfaces should be clean, dry and free of dust, grease, wax or other contaminants. Previously painted surface should be scrapped, cleaned and repaired where necessary with a spackling compound to ensure a smooth, sound surface before applying paint. Dull glossy surfaces by fine sandpaper. Prime where necessary. Shellac all knots and prime bare wood with an oil-based primer. Plaster must age at least 30 days and be thoroughly dry before painting. Metal surfaces should be removed of all rust and cleaned. Prime with an appropriate metal primer.

**APPLICATION:** Apply at surface temperature of 0 C or higher. May be applied by brush, roller, or spray. Stir product with a circular, lifting motion prior to using the product. Brush a 4-foot section on the edges and roll in the middle using “W’s” or “M’s”. Fill in the section and always finish on the down stroke from the very top of the wall to the very bottom in one clean motion. Overlap slightly and continue until the wall is finished.

**Brush-**Nylon or Polyester is recommended.

**Roller-** Smooth to medium (5mm-10mm) sleeve is recommended.

**Spray-** (Airless Equipment) - .015" to .019" tip size.

- 2300-2700 p.s.i.

\*Spray recommendations will vary according to manufacturer.

**DRY TIME:** Dry to touch 30 minutes. Recoat 2-4 hours.

**SPREADING RATE:** Up to 440 Sq. ft/ 4 litres yields approx. 4 mils wet (1.32 mils dry) film per coat. Surface texture and porosity will affect actual yield.

**CLEAN UP:** Use warm soapy water to wipe spots and smears immediately and to clean tools.

**THINNING:** Not normally recommended but water if necessary.

**CLEANING MAINTENANCE:** After a period of 30 days, surfaces may be washed periodically. Abrasive cleaners are not recommended.