



**100% ACRYLIC FLAT
LOW TEMPERATURE CURE
1650 SERIES
TECHNICAL DATA**

A quality coating with a beautiful 'matte' finish. This 100% Acrylic coating is able to form a film at temperatures as low as 0°C (excellent for unheated Underground parking garages). Excellent adhesion to sound and properly prepared substrates. Exhibits excellent flexibility and crack resistance and has exceptionally low V.O.C. (Eco-friendly). Protek's product also exhibits excellent dirt pick-up resistance and is non-yellowing.

SPECIFIC GRAVITY: 1.3

GLOSS: 5-10 @ 60°.

VISCOSITY: 95-100KU

SURFACE PREPARATION:

All surfaces should be clean, dry and free of dust, grease, wax or other contaminants. Previously painted surface should be scrapped, cleaned and repaired where necessary with a spackling compound to ensure a smooth, sound surface before applying paint. Dull glossy surfaces by fine sandpaper. Prime where necessary.

APPLICATION: Apply at air temperature of 0 C or higher. May be applied by brush, roller, or spray.

Stir product with a circular, lifting motion prior to using the product.

Brush-Polyester or polyester/nylon is recommended.

Roller- Medium sleeve is recommended.

Spray- (Airless Equipment) - .011" to .015" tip size.

- 2000-2500 p.s.i.

DRY TIME: Dry to touch 1-2 hours. Recoat 2-4 hours.

SPREADING RATE: Up to 450 Sq. ft/ 4 litres yields approx. on a sealed surface. Surface texture and porosity will affect actual yield.

CLEAN UP: Use warm soapy water to wipe spots and smears immediately and to clean tools.

THINNING: Not normally recommended but water if necessary.

CLEANING MAINTENANCE: After a period of 30 days, surfaces may be washed periodically. Abrasive cleaners are not recommended.