



PROTEK STEP
EPOXY MODIFIED ACRYLIC WHITE BASE
6170 SERIES
TECHNICAL DATA

Ultra Premium quality Acrylic latex floor coating modified with Epoxy Ester. Flat like finish with exceptionally low odour. A finish coat for suitably prepared floors interior/exterior excellent in garages, basements, balconies and many industrial floor applications. Dries and cures really quickly without much odour. An ideal coating for basement floors and exterior cement porches, steps. Allows cement surfaces to breathe, therefore allowing moisture to pass through. Resists 'pockets' popping up. Can be tinted to most pastel colours to medium colours. Also available in Clay and Green both for tennis courts with little or no glare from sun light.

SPECIFIC GRAVITY: 1.10

GLOSS: 5@ 60°

FLASH POINT: NONE

VISCOSITY: 60-65 KU

SURFACE PREPARATION:

All surfaces should be clean, dry and free of dust, grease, wax or other contaminants. Previously painted surface should be scrapped, cleaned and repaired where necessary with a spackling compound to ensure a smooth, sound surface before applying paint. Dull glossy surfaces by fine sandpaper. Extremely smooth cement should also be mechanically abraded before painting and first coat should be thinned or an Epoxy primer applied first. Metal surfaces should be removed of all rust and cleaned. Prime with an appropriate metal primer.

APPLICATION: Apply at air temperature of 10 C or higher. May be applied by brush, roller, or spray. Stir product with a circular, lifting motion prior to using the product. Brush a 4-foot section on the edges and roll in the middle using "W's" or "M's". Fill in the section and always finish towards yourself one clean motion. Overlap slightly and continue until the floor is finished. Must go at right angle for second coat to even the finish. Always finishing closest to the door.

Brush-Pure bristle or Polyester is recommended.

Roller- Smooth to medium (5mm-13mm) sleeve is recommended.

DRY TIME: Dry to touch 1-2 hours. Under normal conditions.

Recoat 2-4 hours.

SPREADING RATE: Up to 300 Sq. ft/ 4 litres yields approx. 5 mils wet (1.65 mils dry) film per coat. Surface texture and porosity will affect actual yield.

CLEAN UP: Use mineral spirits to wipe spots/smears and to clean tools.

THINNING: Not normally required but where necessary small amount of mineral spirits.

CLEANING MAINTENANCE: After a period of 30 days, surfaces may be washed periodically. Abrasive cleaners are not recommended.