

Technical Data Sheet NR 9925

ADHESION ADDITIVE FOR GLASS

Creation date: 22/01/1999 Revision date: 29/4/2009, version 3

ICA S.p.a. Via S. Pertini n. 52, Zona Ind.le A 62012 Civitanova Marche (MC) - Italy
Tel. +39 0733 8080 Fax. +39 0733 808140

PRODUCT: AD33 ADHESION ADDITIVE FOR GLASS

DESCRIPTION: This additive promotes adhesion onto glass of water based products, thanks to a particular process which comes about between the additive, the resin and the substrate.

SPECIFICATIONS OF SUPPLIED PRODUCT

Physical state: clear liquid

APPLICATION: AD33 should be added at 2% in weight to water based coatings for glass form the GPAO, GPTSA, GPVMA series. The additive should be incorporated very carefully, with a mechanical spindle (our 006D08001)

SHELF LIFE AT 20°C: 12 months in correctly stored unopened tin

NB:

- to obtain good adhesion on glass the mixture of product GPAO, or GPTSA or GPVMA and AD33 must be topped up after 24-48 at 25°C from its initial mixture. It is not advisable to add the additive more than twice to the same first component.
- Keep away from water and particularly damp places. Keep the containers tightly closed.

SPECIFICATIONS OF SUPPLIED PRODUCT

CHARACTERISTICS	UNITS	VALUE	METHOD
Specific gravity at 20°C:	g/ml	1.06 ± 0.05	MP01

Always verify the suitability of the product for the job to be done before application. We can not accept responsibility for the outcome.

The information contained in this technical data sheet, as well as any verbal information, is given to the best of our knowledge. We do not accept responsibility for obsolete or incorrect information. The information is to be considered obsolete when a new technical data sheet is issued. Please feel free to contact us to request the latest edition.

AD33/3

Pagina 1 di 1